

Polyethylene Film	Dual-Extruded
UV Protection	HALS
Colour	Light Grey / Black
Thermal Properties	Vicat Softening Point (1kg) 93°C
Cold Crack Temperature	-25°C
500 microns thickness	Bubble Film = 300 micron +/- 10% Back film = 240 micron +/- 10%
Weight per m²	520gms +/- 10%
Overall Bubble Width	2500mm +/- 1%
Welding Edges	50mm +/- 10%
Overall Width	2600mm +/- 10%
Roll Diameter	0.80m +/- 1%
Roll Length	90m +/- 2%
Est. Quantity for 120m³ truck	2.5m = 14,535m ² = 57 rolls
Est. Quantity Containers	$20\text{ft} = 4,050\text{m}^2 = 18 \text{ rolls}$ $40\text{ft} = 10,125\text{m}^2 = 45 \text{ rolls}$
Packaging	Packaged in Polyethylene bags
Core Diameters	Internal 76mm/External 80mm
Identification	Batch Identification by Q.A. slip and label showing Length/Grade
Warranty	10 year pro rata warranty
GEOBUBBLE™TECHNOLOGY	
Bubble Width x Length	15x30mm
Bubble Height	5.5mm
No. of bubble per m²	1029

